



PSR 134 Phenolic Resin

PSR134 is a plasticized, latent curing phenolic liquid resin that displays an outstanding combination of strength, toughness, high temperature resistance and flame resistance. It can be used with glass as well as carbon fabrics.

Properties of PSR134 Liquid Phenolic Resin

Solids %	67 - 71%
Brookfield Viscosity, 25°C, cps	1700 - 2300 cps
Solvent	Methanol
Recommended Storage	40°F
Shelf Life at 40°F	3 Months
Shelf Life at 77°F	3 Weeks
Packaging Options	Drums, Totes, Tankers

NOTE: The data presented herein has been developed under controlled manufacturing and test conditions and is considered accurate. No warranty is expressed or implied regarding the accuracy or use of this data or the use of this product. It is the responsibility of the end user to determine suitability for use.